

## VALVE BODY & BOLTING TEMPERATURE RATINGS

### VALVE BODY MATERIAL TEMPERATURE RANGE ASME B16.34

Material	Lower Temp.	Upper Temp.
Cast Iron	-18°C	210°C
Ductile Iron	-20°C	343°C
Carbon Steel - Grade A216 - WCB	-29°C	425°C
Carbon Steel - Grade A352 - LCB	-46°C	345°C
Carbon Moly - Grade A217 - WC1 (1)	-29°C	538°C
1 ¼ Cr - ½ Mo - Grade A217 - WC6 (2)	-29°C	595°C
2 ¼ Cr - 1 Mo - Grade A217 - WC9 (2)	-29°C	595°C
5 Cr - ½ Mo - Grade A217 - C5 (2)	-29°C	650°C
9 Cr - 1 Mo - Grade A217 - C12 (2)	-29°C	650°C
Type 304 SS - Grade A351 - CF8 (2/3)	-254°C	816°C
Type 347 SS - Grade A351 - CF8C (2/4)	-254°C	816°C
Type 316 SS - Grade A351 - CF8M (2/3)	-254°C	816°C
3 ½ Ni - Grade A352 - LC3	-101°C	345°C
Aluminium	-198°C	204°C
Bronze	-198°C	288°C
Inconel	-198°C	649°C
Monel	-198°C	450°C
Hastelloy B	-198°C	371°C
Hastelloy C	-198°C	538°C
Titanium		316°C
Nickel	-198°C	260°C
Alloy 20 - Grade A351 - CN7M	-46°C	325°C
Alloy 20 - Grade A990 - CN3MCu	-29°C	320°C

Notes per ASME B16.34-2009:-

- (1) Not suitable for prolonged exposure above 470°C.
- (2) Flanged ends in 150 class ratings terminate at 538°C.
- (3) At temperatures above 538°C carbon content must be > 0.04%.
- (4) At temperatures above 538°C consult ANSI B16.34 for heat treatment requirements.

### VALVE TRIM MATERIAL TEMPERATURE RANGE

Material	Lower Temp.	Upper Temp.
Type 304 SS	-232°C	600°C
Type 316 SS	-232°C	600°C
Hastelloy B	-195°C	371°C
Hastelloy C	-195°C	538°C
Alloy 20	-46°C	316°C
Type 416, F6A, 410 SS*	-29°C	427°C
TFE	-200°C	220°C
Buna-N / NBR	-46°C	150°C

Note:- Cold working pressure rating (CWP) decreases as temperature increases. Refer to ASTM P/T charts.

\*Minimum Temperature will vary from -100°C to 0°C according to grade of CR13 and treatment. Must be Charpy impact tested if lower than -29°C. Many of the above valve body and trim material temperatures are indicative and can vary widely depending on manufacturers:- grade, form, class of valve, end connections, duration, carbon content, annealing process, impact testing, fluid type, application etc.

## VALVE MATERIALS & CORRESPONDING BOLTING COMBINED TEMPERATURE RANGE

Valve Body Material	Corresponding Bolting	Material Nuts	Lower Temp.	Upper Temp.
Grade WCB (Carbon Steel)	ASTM A193 Gr B7*	ASTM A194 G2 2H	-29°C	427°C
Grade LCB (Carbon Steel)	ASTM A320 Gr L7†	ASTM A194 Gr 4	-46°C	343°C
Grade WC1 (Carbon Moly)	ASTM A193 Gr B7*	ASTM A194 Gr 2H	-29°C	400°C
	ASTM A193 Gr B16	ASTM A194 Gr 4	-29°C	454°C
Grade WC6 (1 ¼ Cr-½ Mo)	ASTM A193 Gr B7*	ASTM A194 Gr 2H	-29°C	400°C
	ASTM A193 Gr B16	ASTM A194 Gr 4	-29°C	593°C
Grade WC9 (2 ¼ Cr-1 Mo)	ASTM A193 Gr B7	ASTM A194 Gr 2H	-29°C	400°C
	ASTM A193 Gr B16	ASTM A194 Gr 4	-29°C	593°C
Grade C5 (5Cr-½ Mo)	ASTM A193 Gr B7*	ASTM A194 Gr 2H	-29°C	400°C
	ASTM A193 Gr B16	ASTM A194 Gr 4	-29°C	593°C
Grade C12 (9Cr-1 Mo)	ASTM A193 Gr B7	ASTM A194 Gr 2H	-29°C	400°C
	ASTM A193 Gr B16	ASTM A194 Gr 4	-29°C	593°C
Grade CF8 (Type 304)	ASTM A320 Gr B8***	ASTM A194 Gr 8	-254°C	575°C
	ASTM A193 Gr B8**	ASTM A194 Gr 8	-150°C	650°C
Grade CF8M (Type 316)	ASTM A320 Gr B8M***	ASTM A194 Gr 8M	-250°C	575°C
	ASTM A193 Gr B8M**	ASTM A194 Gr 8M	-150°C	750°C
Grade LC3 (3½ Ni)	ASTM A320 Gr L7†	ASTM A194 Gr 4	-101°C	343°C

\*Alloy steel bolting, A193 Gr B7 bolts and A194 Gr 2H nuts can only be used at moderate temperatures depending on the permissible differential expansion of valve design which may vary between manufacturers.

\*\*ASTM A193 Gr B8/B8M bolting can rate from -198°C to 800°C, however many manufacturers of bolts and/or valves specify the narrower rating range shown.

\*\*\*For temperatures lower than -200°C (-325°F) ASTM A320 Gr B8/B8M bolting must be impact tested.

†All L7 bolts and Grade 4 nuts must be charpies impact tested for service temperature lower than -29°C.

The above chart shows the combined temperature range, taking into account the valve and bolting material ratings. Refer to ASTM pressure/temperature charts. For limitations of usage and strength levels refer ANSI B16.34.

Where austenitic bolting materials have be carbide solution treated but not strain hardened, they are designated Class 1 or Class 1A. Where austenitic bolting materials have been carbide solution treated and strain hardened, they are designated Class 2. In B8 and B8M, 'Class 2' is recommended for higher classes 900lb and above in larger sizes depending on temperature due to it's higher tensile strength (carbide solution treated, strain hardened).

A193 Gr B7 and Gr L7 are acceptable for NACE (as class III NACE Bolting) service as bolting is "Non wetted parts", however if bolts themselves must conform to NACE then B7M, L7M bolts are required. B8M bolting (same service as 316) conforms to NACE.

Temperature range of studs can vary widely depending on size, stud, manufacturer, bonnet enclosure and valve manufacturers calculation. Also refer to ASTM standard for 'design temperature rating' of bolting.

Go to <https://globalsupplyline.com.au/catalogue-gsl-valve-api603/> for ASME B16.34 pressure/temperature valve rating charts and numerous other related technical valve charts.

For cross reference tables and charts of ASTM/ANSI specifications covering equivalent materials used for valves, flanges & fittings go to: - <https://globalsupplyline.com.au/stainless-valve-grades/>

## ASTM MATERIALS SPECIFICATIONS AND PRESSURE TEMPERATURE CATEGORIES B16.34 - 2009

Material Group	Nominal Designation	Pressure - Temp. Ratings	Applicable ASTM Specifications		
			Forgings	Castings	Plate
1.1	C - Si	2 - 1.1	A 105	A 216 Gr. WCB	A 515 Gr. 70
	C - Mn - Si		A 350 Gr. LF2		A 516 Gr. 70
	3½ Ni		A 350 Gr. LF3		A 537 Cl. 1
1.2	C - Mn - Si	2 - 1.2		A 216 Gr. WCC	
				A 352 Gr. LCC	
	C - Mn - Si - V		A 350 Gr. LF6 Cl. 2		
	2½ Ni			A 352 Gr. LC2	A 203 Gr. B
	3½ Ni		A 352 Gr. LC3	A 203 Gr. E	
1.3	C - Si	2 - 1.3		A 352 Gr. LCB	A 515 Gr. 65
	C - Mn - Si				A 515 Gr. 65
	C - ½Mo			A 217 Gr. WC1/A352 LC1	
1.4	C - Si	2 - 1.4			A 515 Gr. 60
	C - Mn - Si		A 350 Gr. LF1		A 515 Gr. 60
1.5	C - ½Mo	2 - 1.5	A 182 Gr. F1		A 204 Gr. A
					A 204 Gr. B
1.7	C - ½Mo	2 - 1.7			
	½Cr - ½Mo		A 182 Gr. F2		
	Ni - ½Cr - ½Mo			A 217 Gr. WC4	
	¾Ni - ¾Cr - Mo			A 217 Gr. WC5	
1.9	1¼Cr - ½Mo			A 217 Gr. WC6	
	1¼Cr - ½Mo - Si		A 182 Gr. F11 Cl. 2		A 387 Gr. 11 Cl. 2
1.10	2¼Cr - 1Mo	2 - 1.10	A 182 Gr. F22 Cl. 3	A 217 Gr. WC9	A 387 Gr. 22 Cl. 2
1.11	3Cr - 1Mo	2 - 1.11	A 182 Gr. F21		A 204 Gr. C
1.13	5Cr - ½Mo	2 - 1.13	A 182 Gr. F5A	A 217 Gr. C5	
1.14	9Cr - 1Mo	2 - 1.14	A 182 Gr. F9	A 217 Gr. C12	
1.15	9Cr - 1Mo - V	2 - 1.15	A 182 Gr. F91	A 217 Gr. C12A	A 387 Gr. 91 Cl. 2
1.17	1Cr - ½Mo	2 - 1.17	A 182 Gr. F12 Cl. 2		
	5Cr - ½Mo		A 182 Gr. F5		
2.1	18Cr - 8Ni	2 - 2.1	A 182 Gr. F304	A 351 Gr. CF8	A 240 Gr. 304
			A 182 Gr. F304H	A 351 Gr. CF10	A 240 Gr. 304H
2.2	16Cr - 12Ni - 2Mo	2 - 2.2	A 182 Gr. F316	A 351 Gr. CF8M	A 240 Gr. 316
			A 182 Gr. D316H	A 351 Gr. CF10M	A 240 Gr. 316H
	18Cr - 8Ni			A 351 Gr. CF3A	
	18Cr - 13Ni - 3Mo		A 182 Gr. F317		A 240 Gr. 317
	18Cr - 13Ni - 3Mo		A 182 Gr. 317H	A 351 Gr. CF8A	A 240 Gr. 317H
	19Cr - 10Ni - 3Mo			A 351 Gr. CG8M	
2.3	18Cr - 8Ni	2 - 2.3	A 182 Gr. F304L	A 351 Gr. CF3	A 240 Gr. 304L
	18Cr - 13Ni - 3Mo		A 182 Gr. F317L		
	16Cr - 12Ni - 2Mo		A 182 Gr. F316L	A 351 Gr. CF3M	A 240 Gr. 316L
2.4	18Cr - 10Ni - Ti	2 - 2.4	A 182 Gr. F321		A 240 Gr. 321
			A 182 Gr. F321H		A 240 Gr. 321H
2.5	18Cr - 10Ni - Cb	2 - 2.5	A 182 Gr. F347	A 351 Gr. CF8C	A 240 Gr. 347
			A 182 Gr. F347H		A 240 Gr. 347H
			A 182 Gr. F348		A 240 Gr. 348
			A 182 Gr. F348H		A 240 Gr. 348H
2.7	25Cr - 20Ni	2 - 2.7	A 182 Gr. F310H		A 240 Gr. 310H
2.8	20Cr - 18Ni - 6Mo	2 - 2.8	A 182 Gr. F44	A 351 Gr. CK3MCuN	A 240 Gr. S31254
	22Cr - 5Ni - 3Mo - N		A 182 Gr. F51	A 351 Gr. CD3MN	A 240 Gr. S31803
	25Cr - 7Ni - 4Mo - N		A 182 Gr. F53		A 240 Gr. S32750
	24Cr - 10Ni - 4Mo - V			A 351 Gr. CE8MN/CD4MCuN	
	25Cr - 5Ni - 2Mo - 3Cu			A 995 Gr. 1B	
	25Cr - 7Ni - 2.5Mo - W - Cb			A 995 Gr. CD3MWCuN/6A	
	25Cr - 7.5Ni - 3.5Mo - N - Cu - W		A 182 Gr. F55		A 240 Gr. S32760

## ASTM MATERIALS SPECIFICATIONS AND PRESSURE TEMPERATURE CATEGORIES B16.34 (Cont'd)

Material Group	Nominal Designation	Pressure - Temp. Ratings	Applicable ASTM Specifications		
			Forgings	Castings	Plate
3.1	35Ni - 35Fe - 20Cr - Cb	2 - 3.1	B 462 Gr. N08020		B 463 Gr. N08020
3.2	99.0Ni	2 - 3.2	B 564 Gr. N02200		B 162 Gr. N02200
3.3	99.0Ni - Low C	2 - 3.3			B 162 Gr. N02201
3.4	67Ni - 30Cu	2 - 3.4	B 564 Gr. N04400	A 494 Gr. M-35-1	B 127 Gr. N04400
	67Ni - 30Cu - S			A 494 Gr. M-35-1	
3.5	72Ni - 15Cr - 8Fe	2 - 3.5	B 564 Gr. N06600		B 168 Gr. N06600
3.6	33Ni - 42Fe - 21Cr	2 - 3.6	B 564 Gr. N08800		B 409 Gr. N08800
3.7	64Ni - 29.5Mo - 2Cr -2Fe-Mn-W	2 - 3.7	B 462 Gr. N10675		B 333 Gr. N10675
	65Ni - 28Mo - 2Fe		B 564/B462 Gr. N10665		B 333 Gr. N10665
3.8	42Ni - 21.5Cr - 3Mo - 2.3Cu	2 - 3.8	B 564 Gr. N08825		B 424 Gr. N08825
	54Ni - 16Mo - 15Cr		B564/B462 Gr. N10276		B 575 Gr. N10276
	55Ni - 21Cr - 13.5Mo		B 462 Gr. N06022		B 575 Gr. N06022
	55Ni - 23Cr - 16Mo - 1.6Cu		B 462 Gr. N06200		B 575 Gr. N06200
	60Ni - 22Cr - 9Mo - 3.5Cb		B 564 Gr. N06625		B 443 Gr. N06625
3.10	25Ni - 46Fe - 21Cr - 5Mo	2 - 3.10			B 599 Gr. N08700
3.11	44Fe - 25Ni - 21Cr - Mo	2 - 3.11			B 625 Gr. N08904
3.13	Ni - Fe - Cr - Mo - Cu - Low C	2 - 3.13	B 564 Gr. N08031		B 625 Gr. N08031
3.14	40Ni - 29Cr - 15Fe - 5Mo	2 - 3.14	B 462 Gr. N06030		B 582 Gr. N06030
3.15	42Ni - 2Fe - 21Cr	2 - 3.15	B 564 Gr. N08810		B 409 Gr. N08810
	Ni - Mo			A 494 Gr. N-12MV	
	Ni - Mo - Cr			A 494 Gr. CW-12MW	
3.17	29Ni - 20½Cr - 3½Cu - 2½Mo	2 - 3.17		A 351 Gr. CN7M	
3.19	57Ni - 22Cr - 14W - 2Mo - La	2 - 3.19	B 564 Gr. N06230		

*Global Supply Line Pty Ltd Australia  
Largest valve stockist in the Southern Hemisphere - shipping worldwide.  
View our stock lists at our website.*

[www.globalsupplyline.com.au](http://www.globalsupplyline.com.au)

*At Global Supply Line the same knowledge and effort we put into this website goes into every product we sell. If this website helps you, please reward Global Supply Line with your business and advise your purchasing staff, plant managers and project managers about us.*

*For other ANSI, ASME, ISO and API, valve related technical cross references relating to pressure, temperature, application, suitability, equivalents, valve body & trim materials, valve manufacturing & test standards go to the technical section our website.*

*We stock valves in A105, LF2, 304, 304L, 316, 316L, F51, CF8, CF3, F82, WC5, WC6, WC9, F11, F5, Bronze, Iron, etc. in Ball, Butterfly, Check, Control, Gate, Globe, Needle, Parallel slide, Plug, etc. Valves are manufactured to API 600, API 602, API 603, API 6A, API 6D, BS1868 and numerous other standards.*

*If we don't have the valve in stock, we can source it from our overseas network of stockists and very short lead-time specialty manufacturers. We can even supply exotic grades like Nickel, Super Duplex F55 and Monel (ASTM A494-M35-1) Cd4M-Cu, Hastelloy C (ASTM A-494 CW12MW), 317 (C8G8M).*

### DISCLAIMER:-

This is a general overview. Information provided should not be used to make your operational or design decision. We accept no liability or responsibility for the information and do not guarantee it's correctness.